



Park Lane Bathstone Top Bed



Description	Cream limestone; uniform with some calcite veins	
Country of Origin	UK	
Geological Type	Oolitic Limestone	
Colour	Warm Honey/cream	
Density	2000 kg/m ³	BSEN 1936
Compressive Strength	23MPa	EN772-1
Water Absorption at atmospheric pressure	11.7% by mass	BSEN 13755
Open Porosity	25.6%	BS EN 1936
Flexural Strength under conc. load:	3.4 MPa perpendicular to bed	BSEN 12372
Average Block Size	1500L x 1000W x 700H	
Saturation coefficient	0.87	BRE 141

Mine Location:

Park Lane Mine Brockleaze Neston Corsham
SN13 9TW Wiltshire England

01844 279274

www.parklanebathstone.co.uk
sales@parklanebathstone.co.uk